

Product specification

Material AEROSIL® 300 Pharma
Spec.Code K00

Evonik Resource Efficiency GmbH

Business Line Silica

www.evonik.com

Contact: specification-silica@evonik.com

Inspection Characteristics	Method	Limits	Units	Z
Specific surface area	ISO 9277, modified	270-330	m ² /g	X
Identification	tested acc. to Ph.Eur.	pass		C
Assay (SiO ₂ content)	tested acc. to Ph.Eur.	99.0-100.5	%	X
pH value	tested acc. to Ph.Eur.	3.5-5.5		X
Chlorides <=250ppm	tested acc. to Ph.Eur.	pass		C
Loss on ignition	tested acc. to Ph.Eur.	<=5.0	%	X
Identification (1),(2) and (3)	tested acc. to JP	pass		C
Loss on drying	tested acc. to JP	<=7.0	%	X
Loss on ignition	tested acc. to JP	<=12.0	%	X
Al content	tested acc. to JP	pass		C
Fe content <=500ppm	tested acc. to JP	pass		C
Ca content	tested acc. to JP	pass		C
As content <=5ppm	tested acc. to JP	pass		C
Cl content <=0.011%	tested acc. to JP	pass		C
Heavy metals <=40ppm	tested acc. to JP	pass		C
Assay (SiO ₂ content)	tested acc. to JP	>=98.0	%	X
Volume test >=70ml	tested acc. to JP	pass		C
As content <=8ppm	tested acc. to USP/NF	pass		C
Loss on drying	tested acc. to USP/NF	<=2.5	%	X
Loss on ignition	tested acc. to USP/NF	<=2.0	%	X
Identification, A and B	tested acc. to USP/NF	pass		C
pH value	tested acc. to USP/NF	3.5-5.5		X
Assay (SiO ₂ content)	tested acc. to USP/NF	99.0-100.5	%	X

Report on inspection certificate: X = specific/actual value, C = unspecific value/conformity, T = not reported

White, fine, amorphous powder.

Elemental Impurities:

Elemental Impurities are not intentionally added to the production process.

The elemental impurities of the ICH Q3D are tested on a regular basis acc. to USP 233 and Ph. Eur. 5.20.

Residual solvents:

No organic solvents are used in the manufacture of above mentioned product. For this reason, constitutionally no residual solvents as cited in recent versions of the European Pharmacopoeia, (class 1, 2 and 3 or other solvents, USP chapter 467), 2008 and amendments are present in

Material: AEROSIL® 300 Pharma		Spec-Code: K00	Page 1 from 2
Print date: 12.07.2018	Valid from: 12.07.2018	Version: 9	

concentration about the control limits quoted in USP. For above mentioned product class 1 residual solvents are tested on a regular basis according to USP/NF: Carbon tetrachloride, 1,2 Dichlorethane, 1,1 Dichlorethene, 1,1,1 Trichlorethane and Benzene.

TSE/BSE and materials of plant origin:

No raw materials of animal or plant origin (as mentioned in EMEA/410/01, current version) are used in the production process of AEROSIL® Pharma products. AEROSIL® Pharma products have not been in contact with and constitutionally do not include any material of animal or plant origin.

We generally do not use any material of animal or plant origin in our production facilities. AEROSIL® Pharma products are not contaminated with material of animal or plant origin when they leave our production and warehouses.

This product is manufactured in Site Rheinfelden, Untere Kanalstrasse 3, 79618 Rheinfelden, Germany.

This document is computer printed and therefore valid without signature.

All warranty claims in respect of the conformity of our product are subject to our General Terms and Conditions of Sale and Delivery. The data listed above reflects the criteria for our internal quality tests. We do not hereby make any express or implied warranty, whether for specific properties or for fitness for any particular application or purpose. All values are valid for the product when despatched from the works.

The Standard Test Methods can be obtained from specialized publishers. Evonik's test methods are available on request.

Material: AEROSIL® 300 Pharma		Spec-Code: K00
Print date: 12.07.2018	Valid from: 12.07.2018	Version: 9